

DESCRIPTION

DISCOLORATION REMOVAL CLEANING AGENT FOR TITANIUM AND
TITANIUM ALLOY BUILDING MATERIALS, AND
5 DISCOLORATION REMOVAL CLEANING METHOD

FIELD OF THE INVENTION

The present invention relates to a cleaning agent
which exhibits an effect of removing discolored sections
on the surfaces of titanium and titanium alloy building
10 materials used for prolonged periods in outdoor
applications, such as roofs, walls, monuments and the
like, in order to restore the surfaces to a pre-
discolored condition, while also enhancing the
discoloration resistance after cleaning.

15 BACKGROUND ART

Titanium is used as a material for the construction
of structures such as roofs and walls in seashore areas
because of its excellent corrosion resistance against
20 chlorides. Approximately 10 years have passed since the
introduction of titanium for use in roofs and the like,
and not a single case of corrosion has been reported.

Nevertheless, depending on the surrounding
environment, titanium surfaces used for extended periods
25 of time often exhibit discoloration to a dark gold
color. This discoloration occurs due to the growth of
an approximately 10 nm-thick titanium oxide layer on the
titanium surface, with the discoloration producing a
buffering effect which limits discoloration only to the
30 outermost surface layer and therefore does not impair
the anticorrosion effect of the titanium. However, it

poses a problem from an aesthetic standpoint.

Since such discoloration is produced by growth of a titanium oxide layer on the titanium surface by acid rain which results in a buffering effect, removal of the titanium oxide layer can restore the surface to its condition before discoloration.

However, as titanium oxide is a chemically stable compound, it can only be chemically dissolved by coating the discolored sections with a mixed solution of nitric acid and hydrofluoric acid such as is ordinarily used for acid cleaning steps in titanium production processes. Restoration to the surface condition before discoloration is difficult, however, because the titanium base layer is also considerably dissolved. Mechanical methods also exist, and they include methods of polishing the discolored sections using polishing materials, but because the titanium oxide layer which is responsible for discoloration is only a few tens of nanometers thick, the titanium base layer surface also suffers polishing and surface outer appearance can thereby be altered. Prior art methods have accomplished removal of discolored layers by acid cleaning or polishing, with acceptance of a certain degree of outer appearance alteration of the base metal (for example, Materials and Process, 144th Fall Conference, CAMP-ISIJ Vol15 (2002)-1306).

In addition, a titanium carbide layer in titanium surface which is another cause of discoloration is also present on the surface layer of the titanium base substrate under the titanium oxide layer discoloration. Therefore, as the titanium carbide remains on the

titanium surface layer even after removal of the titanium oxide layer, rediscoloring upon prolonged use can still occur after cleaning.

Thus, removal of discolored sections of titanium
5 and titanium alloy building materials remains a difficult task, while it is even more difficult to enhance discoloration resistance after removal.

In light of these circumstances, it is an object of the present invention to provide a cleaning agent for
10 removing discolored sections produced on the surfaces of titanium and titanium alloy building materials without impairing the outer appearance of the base layers, as well as a discoloration removal cleaning agent and discoloration removal cleaning method which inhibit
15 discoloration after the removal.

DISCLOSURE OF THE INVENTION

As a result of much diligent research directed toward the object of accomplishing removal of
20 discoloration-causing titanium oxide layers and titanium carbide deposition layers on titanium surfaces without impairing the outer appearance of the titanium base layers, and enhancing discoloration resistance after their removal, the present inventors have made the
25 following discovery.

The present inventors have found that, by preparing a cleaning agent as a weakly acidic liquid with appropriate viscosity, it is possible to remove discolored sections of titanium and titanium alloy
30 building materials without their scattering during coating and cleaning. The inventors have also found

that the dryness after coating can be adjusted by adding to the cleaning solution a hydrophilic oxygen-containing hydrocarbon having a water vapor-controlling function.

It was additionally discovered that even extreme

5 discolored sections can be removed by adjusting the aging time after coating. Finally, it was discovered that it is possible to form a protective film on the surface of titanium and titanium alloy building materials by a polishing operation after coating, and
10 that discoloration can thereby be inhibited.

Specifically, based on this acquired knowledge, the present inventors have succeeded in developing a cleaning agent exhibiting the desired effects, comprising a combination of a water-soluble inorganic
15 acid salt, organic acid or organic acid salt, a surfactant and a hydrophilic oxygen-containing hydrocarbon and, if necessary, a thickener, a discoloration inhibitor, a fluoracarbon resin and a polishing material, as well as a cleaning method using
20 the cleaning agent.

The present invention has been completed based on the discoveries mentioned above, and its gist is as follows.

[1] A discoloration removal cleaning agent for
25 titanium and titanium alloy building materials, characterized by comprising at least a water-soluble inorganic acid salt, an organic acid or organic acid salt, a surfactant, a hydrophilic oxygen-containing hydrocarbon solvent, and water.

30 [2] The discoloration removal cleaning agent for titanium and titanium alloy building materials according

to [1] above, characterized in that the cleaning agent satisfies either or both of the following conditions (1) and (2):

5 (1) the cleaning agent comprises one or more types of thickener; and

(2) the viscosity of the cleaning agent (measured at room temperature with a Brookfield viscometer) is 100-10,000 mPa·s.

10 [3] The discoloration removal cleaning agent for titanium and titanium alloy building materials according to [1] or [2] above, characterized in that the cleaning agent satisfies either or both of the following conditions (3) and (4):

15 (3) the cleaning agent comprises one or more types of fluoracarbon resin and one or more types of polishing material; and

(4) the cleaning agent comprises one or more types of discoloration inhibitor.

20 [4] The discoloration removal cleaning agent for titanium and titanium alloy building materials according to [3] above, wherein the content of inorganic fluorine compound salts is 0.5-5.0 wt%.

25 [5] The discoloration removal cleaning agent for titanium and titanium alloy building materials according to any one of [1] to [4] above, wherein the organic acid or organic acid salt is at least one selected from the group consisting of formic acid, oxalic acid, citric acid, malic acid, lactic acid, tartaric acid, succinic acid, fumaric acid, gluconic acid, hydroxybutyric acid,
30 ethylenediaminetetraacetic acid,
hydroxyethylenediaminetetraacetic acid,

diethylenetriaminopentaacetic acid,
hydroxyethanediphosphonic acid, or salts, such as
sodium, potassium and ammonium salts, of these organic
acids.

5 [6] The discoloration removal cleaning agent for
titanium and titanium alloy building materials according
to any one of [1] to [5] above, wherein the content of
the organic acid or organic acid salt is 2-15 wt%.

10 [7] The discoloration removal cleaning agent for
titanium and titanium alloy building materials according
to any one of [1] to [6] above, wherein the surfactant
has an HLB (hydrophilic-lipophilic balance) value of 12
or greater.

15 [8] The discoloration removal cleaning agent for
titanium and titanium alloy building materials according
to any one of [1] to [7] above, wherein the organic acid
or organic acid salt is at least one selected from the
group consisting of anionic surfactants such as
polyoxyethylenealkyl ether acetic acids and their sodium
20 salts, polyoxyethylenealkyl ether phosphoric acids and
their sodium salts, dialkylsulfosuccinic acids and their
sodium salts, and nonionic surfactants such as
polyoxyethylenealkyl ethers, polyoxyethylenealkylallyl
ethers and polyoxyethylenepolyoxypropylenealkyl ethers.

25 [9] The discoloration removal cleaning agent for
titanium and titanium alloy building materials according
to any one of [1] to [8] above, wherein the content of
the surfactant is 2-10 wt%.

30 [10] The discoloration removal cleaning agent for
titanium and titanium alloy building materials according
to any one of [1] to [9] above, wherein the hydrophilic

oxygen-containing hydrocarbon is at least one selected from the group consisting of ethylene glycol, polyethylene glycol, propylene glycol, lower molecular weight polypropylene glycol, hexylene glycol, 1,3-
5 butanediol, glycerin, methyldiglycol, methyltriglycol, ethyldiglycol, ethyltriglycol, butyldiglycol, butyltriglycol and N-methylpyrrolidone.

[11] The discoloration removal cleaning agent for titanium and titanium alloy building materials according
10 to any one of [1] to [10] above, wherein the content of the hydrophilic oxygen-containing hydrocarbon is 5-20 wt%.

[12] The discoloration removal cleaning agent for titanium and titanium alloy building materials according
15 to any one of [1] to [11] above, wherein the thickener is at least one selected from the group consisting of polyvinyl alcohol, methyl cellulose, hydroxyethyl cellulose, guar gum, xanthan gum, carboxyvinyl polymer, polyethylene oxide and polyvinylpyrrolidone.

[13] The discoloration removal cleaning agent for titanium and titanium alloy building materials according
20 to any one of [1] to [12] above, wherein the content of the thickener is 0.2-1.5 wt%.

[14] The discoloration removal cleaning agent for titanium and titanium alloy building materials according
25 to any one of [1] to [13] above, wherein the discoloration inhibitor is at least one selected from the group consisting of mercaptobenzothiazole-based, triazole-based, imidazole-based and thiourea-based
30 discoloration inhibitors.

[15] The discoloration removal cleaning agent for

titanium and titanium alloy building materials according to any one of [1] to [14] above, wherein the content of the discoloration inhibitor is 0.1-1.5 wt%.

5 [16] The discoloration removal cleaning agent for titanium and titanium alloy building materials according to any one of [1] to [15] above, wherein the fluoracarbon resin is at least one selected from the group consisting of polytetrafluoroethylene, polytetrafluoroethylene-hexafluoropropylene copolymer
10 and polyvinylidene fluoride.

[17] The discoloration removal cleaning agent for titanium and titanium alloy building materials according to any one of [1] to [16] above, wherein the content of the fluoracarbon resin is 0.3-2.0 wt%.

15 [18] The discoloration removal cleaning agent for titanium and titanium alloy building materials according to any one of [1] to [17] above, wherein the polishing material is at least one selected from the group consisting of diamond, emery, garnet, corundum, ruby,
20 silica sand, silicon carbide, alundum, cerium oxide, zirconium oxide, γ -alumina and chromium oxide.

[19] The discoloration removal cleaning agent for titanium and titanium alloy building materials according to any one of [1] to [18] above, wherein the content of
25 the polishing material is 10-30 wt%.

[20] The discoloration removal cleaning method for titanium and titanium alloy building materials, wherein discolored sections of a titanium or titanium alloy building material are coated with the discoloration
30 removal cleaning agent according to any one of [1] to [19] above and allowed to stand for a prescribed period

of time, and then the cleaning agent is removed by water washing of the coated sections.

[21] The discoloration removal cleaning method for titanium and titanium alloy building materials according to [20] above, wherein the discoloration removal cleaning agent coated on the discolored sections of the titanium or titanium alloy building material is removed by high-pressure water washing (approximately 30-100 kg/cm², approximately 10-50 L/min) or low-pressure spray water washing (equal to or less than approximately 10 kg/cm², approximately 5-30 L/min) after standing for a prescribed period of time.

[22] The discoloration removal cleaning method for titanium and titanium alloy building materials according to [20] or [21] above, characterized in that the coated sections are subjected to polishing after the coating, if necessary after standing for a prescribed period of time, before water washing.

[23] The discoloration removal cleaning method for titanium and titanium alloy building materials according to [22] above, wherein the discoloration removal cleaning agent is removed by water washing after polishing.

[24] The discoloration removal cleaning method for titanium and titanium alloy building materials according to any one of [20] to [23] above, wherein the coating coverage of the discoloration removal cleaning agent is 50-200 g/m².

30 DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

The discoloration removal cleaning agent for

discolored sections of titanium and titanium alloy building materials according to the invention (hereinafter referred to simply as "discoloration removal cleaning agent") exhibits a powerful
5 discoloration removal effect for titanium and titanium alloy building materials by interaction between multiple cleaning components, and removal of the discolored sections of titanium and titanium alloy building materials is accomplished by combination of the water-
10 soluble inorganic acid salt, organic acid or organic acid salt with the discolored sections of the titanium building material and also by the cleaning power of the water and the surfactant.

The discoloration removal cleaning agent of the invention comprises an inorganic acid salt, organic acid
15 or organic acid salt, a surfactant, a hydrophilic oxygen-containing hydrocarbon (solvent) and water. The acidity of the cleaning agent is preferably pH 4.0-5.5 because the cleaning and removal effect for discolored
20 sections of titanium and titanium alloy building materials is maximized in this range. If necessary, the acidity of the cleaning agent may be adjusted to within this range using an alkaline aqueous solution. Ammonia water is preferred as an alkaline aqueous solution, but
25 caustic soda, bicarbonate soda and similar alkali solutions may also be used.

The components of the discoloration removal cleaning agent of the invention will now be explained.

An inorganic acid salt used in the discoloration
30 removal cleaning agent of the invention has the function of removing discoloration on titanium and titanium alloy

building materials, and it is preferably an inorganic fluorine compound salt (sodium salt, potassium salt, ammonium salt) which reacts with discolored sections. As examples of salts of inorganic fluorine compounds there may be mentioned sodium fluoride, potassium fluoride, ammonium fluoride, ammonium borofluoride, ammonium silicofluoride and the like, which may be used alone or in combinations of more than one. The content of fluorine compound salts in the discoloration removal cleaning agent of the invention will depend on the degree of discoloration of the discolored sections of the titanium or titanium alloy building material, but it is preferably 0.5-5.0 wt% and more preferably 0.7-3.0 wt%. It is preferably not less than 0.5 wt% because the discoloration removal effect will be weakened, while it is also preferably not greater than 5.0 wt% because the solubility in water will be reduced.

Organic acid and organic acid salts used in the discoloration removal cleaning agent of the invention have the function of converting calcium included in the titanium oxide layer of the discolored sections of the titanium or titanium alloy building material into calcium salts and dissolving or dispersing them into the cleaning agent, and they serve as discoloration removal aids. As examples of organic acids there may be mentioned formic acid, oxalic acid, citric acid, malic acid, lactic acid, tartaric acid, succinic acid, fumaric acid, gluconic acid, hydroxybutyric acid, ethylenediaminetetraacetic acid, hydroxyethylenediaminetetraacetic acid, diethylenetriaminopentaacetic acid and

hydroxyethanediphosphonic acid, while sodium, potassium and ammonium salts may be mentioned as their salts. One or more of these organic acids and organic acid salts may be used.

5 The content of organic acids and organic acid salts in the discoloration removal cleaning agent of the invention will depend on the degree of discoloration of the discolored sections of the titanium or titanium alloy building material, but it is preferably 2-15 wt%
10 and more preferably 3-10%. It is preferably not less than 2 wt% because the calcium removing power will be weakened, while it is preferably not greater than 15 wt% because the solubility in water will be reduced.

 A surfactant used in the discoloration removal
15 cleaning agent of the invention improves the permeability and wettability of the cleaning agent in the discolored sections of titanium and titanium alloy building materials by reducing the interfacial tension of the cleaning agent, and thereby exhibits an effective
20 function of maximizing the cleaning effect. Anionic and nonionic surfactants are effective, and the HLB (hydrophilic-lipophilic balance) of hydrophilic groups is preferably 12 or greater. An HLB value of less than 12 is not preferred because it results in poor water
25 solubility.

 As examples of anionic surfactants there may be mentioned polyoxyethylenealkyl ether acetic acids and their sodium salts, polyoxyethylenealkyl ether phosphoric acids and their sodium salts and
30 dialkylsulfosuccinic acids and their sodium salts, and as examples of nonionic surfactants there may be

mentioned polyoxyethylenealkyl ethers,
polyoxyethylenealkylallyl ethers and
polyoxyethylenepolyoxypropylenealkyl ethers. One or
more of these anionic or nonionic surfactants may be
5 used. The surfactant content in the discoloration
removal cleaning agent of the invention is preferably 2-
10 wt% and more preferably 3-6 wt%. It is preferably
not outside of this range because it will become
difficult to achieve the desired effect as a surfactant.

10 A hydrophilic oxygen-containing hydrocarbon
(oxygen-containing hydrocarbon solvent) used in the
discoloration removal cleaning agent of the invention
has the function of controlling evaporation of water,
and addition of a water-soluble oxygen-containing
15 hydrocarbon adjusts the drying property after coating of
the cleaning agent while also improving compatibility
with various compounded ingredients and providing an
anti-freeze function. As examples of hydrophilic
oxygen-containing hydrocarbons there may be mentioned
20 ethylene glycol, polyethylene glycol, propylene glycol,
low molecular weight polypropylene glycol, hexylene
glycol, 1,3-butanediol, glycerin, methyldiglycol,
methyltriglycol, ethyldiglycol, ethyltriglycol,
butyldiglycol, butyltriglycol and N-methylpyrrolidone.
25 One or more types of these hydrophilic oxygen-containing
hydrocarbons may be used. The content of the
hydrophilic oxygen-containing hydrocarbon in the
discoloration removal cleaning agent of the invention is
preferably 5-20 wt% and more preferably 10-15 wt%. It
30 is preferably not outside of this range because it will
become difficult to achieve the desired water vapor-

controlling function.

The water used in the discoloration removal cleaning agent of the invention functions as a solvent, and tap water, ion-exchanged water, distilled water or
5 other types of purified water may be used.

The discoloration removal cleaning agent of the invention may also contain, if necessary, one or more of the following components as additives in addition to the composition described above.

10 A thickener used in the discoloration removal cleaning agent of the invention allows adjustment of the viscosity by the amount of its addition to the discoloration removal cleaning agent, and it exhibits an effect against scattering and dripping. As examples of
15 thickeners there may be mentioned polyvinyl alcohol, methyl cellulose, hydroxyethyl cellulose, guar gum, xanthan gum, carboxyvinyl polymer, polyethylene oxide and polyvinylpyrrolidone. One or more types of these thickeners may be used. The content of the thickener in
20 the discoloration removal cleaning agent of the invention is preferably 0.2-1.5 wt% and more preferably 0.3-1.0 wt%. It is preferably not outside of this range because it will become difficult to achieve the desired effect as a thickener.

25 The viscosity of the discoloration removal cleaning agent of the invention is preferably 100-10,000 mPa·s (measured at ordinary temperature with a Brookfield viscometer, at 30 rpm). Within this range, it is possible to produce a coated film without dispersion of
30 the solution to the surrounding areas during coating, and while avoiding dripping of the solution, especially

when coating vertically standing titanium and titanium alloy building materials; this will aid the function of the discoloration removal cleaning agent.

As discoloration inhibitors to be used in the
5 discoloration removal cleaning agent of the invention there may be mentioned mercaptobenzothiazole-based, triazole-based, imidazole-based and thiourea-based discoloration inhibitors, which are discoloration inhibitors for titanium and titanium alloy building
10 materials. As specific examples there may be mentioned mercaptobenzothiazole propionic acid, mercaptobenzothiazole succinic acid, benzotriazole, methylimidazole, methylmercaptotetrazole, thiourea, dimethylthiourea, trimercapto-S-triazine sodium salt and
15 the like, which may be used alone or in combinations of two or more. The content of discoloration inhibitors in the discoloration removal cleaning agent of the invention is preferably is 0.1-1.5 wt%, and more preferably 0.3-1.0 wt%. It is preferably not outside of
20 this range because it will become difficult to achieve the desired effect as a discoloration inhibitor.

The discoloration removal cleaning agent of the invention can also function as a discoloration inhibitor by addition of a fluoracarbon resin and a polishing
25 material, and subjecting discolored sections to polishing after their cleaning can produce a fluoracarbon resin film on the surface of the discolored sections and thereby prevent further discoloration.

Typical examples of fluoracarbon resins to be used
30 for the invention include polytetrafluoroethylene, polytetrafluoroethylene-hexafluoropropylene copolymer

and polyvinylidene fluoride, and a suitable fluoracarbon resin for the invention is low molecular weight polytetrafluoroethylene which has low surface energy and can effectively prevent production of discoloration substances on the surfaces of titanium and titanium alloy building materials. Lower molecular weight polytetrafluoroethylene may be produced by any method such as telomerization or lower molecularization by radiation cleavage. The lower molecular weight polytetrafluoroethylene preferably has a molecular weight of 2000-500,000 and more preferably 2000-25,000. The lower molecular weight polytetrafluoroethylene may also consist of lower molecular weight polytetrafluoroethylene alone or it may be a commercial product thereof such as a diluted dispersion (for example, a dispersion with a content of 10-20 wt%), and any such commercial products are suitable for use.

The content of the fluoracarbon resin in the discoloration removal cleaning agent of the invention is preferably 0.5-3.0 wt% and more preferably 0.3-2.0 wt%.

Polishing materials to be used for the invention may be selected from among inorganic fine particles of types, hardnesses and fine particle sizes effective for removal of discoloration from the discolored sections of titanium and titanium alloy building materials. As examples there may be mentioned diamond, emery, garnet, corundum, ruby, silica sand, silicon carbide, alundum, cerium oxide, zirconium oxide, γ -alumina and chromium oxide. The hardness of the polishing material is preferably 7 or greater (Mohs hardness) and more preferably 8 or greater (Mohs hardness). A hardness of

less than 7 is not preferred because it will make the effect as a polishing material more difficult to achieve. One or more types of polishing materials may be used, and their mean particle sizes are preferably 1-
5 100 μm and more preferably 30-50 μm . The mean particle sizes are preferably not outside of this range because this may make it difficult to achieve the effect as a polishing material. The polishing material content in the discoloration removal cleaning agent of the
10 invention is preferably 10-30 wt% and more preferably 15-25 wt%. It is preferably not outside of this range because the desired effect as a polishing material becomes difficult to achieve.

A cleaning method employing the discoloration removal cleaning agent of the invention will now be
15 explained.

The discoloration removal cleaning agent of the invention is coated onto the discolored sections of titanium and titanium alloy building materials and then
20 allowed to permeate the discolored sections, so that removal of the discolored sections can be easily accomplished by water washing.

The coating method may be any desired procedure which allows the discoloration removal cleaning agent of
25 the invention to be applied onto discolored sections, but preferred methods are coating with a bristle brush and coating with a sponge roller, painting roller or the like.

The discoloration removal cleaning agent coated on
30 the discolored sections of the titanium or titanium alloy building material is allowed to stand for a

prescribed period of time and is then removed and cleaned by water washing such as, for example, high-pressure water washing (approximately 30-100 kg/cm², approximately 10-50 L/min) or low-pressure spray water washing (equal to or less than approximately 10 kg/cm², approximately 5-30 L/min).

A prescribed period of time for standing after coating of the discoloration removal cleaning agent is effective for permeation and dissolution of the cleaning solution into the discolored sections, and it allows removal of strongly discolored sections to be accomplished more efficiently. The standing time may be selected as appropriate for the discolored section thickness and bonded strength. For example, a short standing time (about 10-15 minutes, for example,) may be sufficient in environments with higher air temperatures (about 25-35°C), while a longer standing time (about 15-30 minutes, for example) may be required in environments with lower air temperatures (about 0-15°C).

The drying after water washing is not particularly restricted so long as it does not adversely affect the surface of the titanium or titanium alloy building material, but natural drying at ordinary temperature is preferred.

A discoloration removal cleaning agent containing a fluoracarbon resin or polishing material according to the invention may also be coated with a bristle brush or with a sponge roller, painting roller or the like. In this case, the cleaning agent will not require a standing time after coating, and polishing may be carried out using a polishing fabric such as a resinous

nonwoven fabric, either manually or with an electric polisher, thereby allowing removal of strongly discolored sections to be efficiently accomplished in a shorter period of time.

5 The water washing after polishing may be removal cleaning by water washing such as, for example, high-pressure water washing (approximately 30-100 kg/cm², approximately 10-50 L/min) or low-pressure spray water washing (equal to or less than approximately 10 kg/cm²,
10 approximately 5-30 L/min). The drying after water washing is not particularly restricted so long as it does not adversely affect the surface of the titanium or titanium alloy building material, but natural drying at ordinary temperature is preferred. The drainage water
15 obtained from the water washing may be neutralized with aqueous slaked lime and subjected to treatment for separation of the precipitate using a flocculating agent or the like.

 The coating coverage of the discoloration removal
20 cleaning agent of the invention will depend on the degree of discoloration of the discolored sections of the titanium or titanium alloy building material, and it may be 50-200 g/m², for example, and is preferably 80-150 g/m².

25 Various improvements or partial modifications and additions may further be incorporated within the scope of the discoloration removal cleaning agent of the invention as described above, so long as the effect of the invention is not notably hindered.

30

EXAMPLES

The present invention will now be explained in greater detail based on the following examples, which are only illustrative and do not restrict the invention in any way.

5 (Composition Example 1)

A discoloration removal cleaning agent of the invention was prepared using the components shown in Table 1.

10

Table 1

Component	Content (wt%)
Sodium fluoride (Morita Chemical Industries Co., Ltd.)	1.0
Potassium fluoride (Morita Chemical Industries Co., Ltd.)	0.9
Ammonium citrate (Fuso Chemical Co., Ltd.)	5.0
Hydroxyacetic acid (70 wt%) (U.S. DuPont Corp.)	4.0
Tetrasodium ethylenediaminetetraacetate (Chelest Corp.)	1.0
Hydroxyethanediphosphonic acid (Nippon Chemical Industrial Co., Ltd.)	1.0
Polyoxyethylene lauryl ether (Lion Corp.)	3.0
Polyoxyethylene lauryl ether acetate (Lion Corp.)	2.0
Mercaptobenzothiazolesuccinic acid (Ciba-Geigy Specialty Chemicals Corp.)	0.3
Dimethylthiourea (Kawaguchi Chemical Industry Co., Ltd.)	0.2
Polyethylene glycol #400 (NOF Corp.)	15.0
Purified water	66.6
	100

Sodium fluoride, potassium fluoride, ammonium citrate, hydroxyacetic acid, tetrasodium ethylenediaminetetraacetate and hydroxyethanediphosphonic acid, weighed out in the proportions listed in Table 1, were placed in a polyethylene container A, the total amount of purified water was added and stirring was effected for complete dissolution of the solid portion.

Next, polyoxyethylene lauryl ether, polyoxyethylene lauryl ether acetate, mercaptobenzothiazolesuccinic acid

and dimethylthiourea, weighed out in the proportions listed in Table 1, were placed in a polyethylene container B, the polyethylene glycol #400 was added and stirring was effected for complete dissolution.

5 The contents of container B were then added to and stirred in the polyethylene container A to prepare a uniform mixed solution.

 The solution resulting after mixing had a viscosity (measured at ordinary temperature with a Brookfield
10 viscometer, at 30 rpm) of 80 mPa·s and a pH of 4.0. A small amount of 28 wt% ammonia water was then added to adjust the pH to 5.0 for use as a discoloration removal cleaning agent (cleaning agent 1).

(Composition Example 2)

15 A discoloration removal cleaning agent of the invention was prepared using the components shown in Table 2.

20

Table 2

Component	Content (wt%)
Ammonium borofluoride (Morita Chemical Industries Co., Ltd.)	0.5
Sodium fluoride (Morita Chemical Industries Co., Ltd.)	1.0
Ammonium citrate (Fuso Chemical Co., Ltd.)	5.0
Hydroxyacetic acid (70 wt%) (U.S. DuPont Corp.)	4.0
Tetrasodium ethylenediaminetetraacetate (Chelest Corp.)	1.0
Hydroxyethanediphosphonic acid (Nippon Chemical Industrial Co., Ltd.)	1.0
Polyoxyethylene lauryl ether (Lion Corp.)	3.0
Polyoxyethylene lauryl ether acetate (Lion Corp.)	2.0
Mercaptobenzothiazolesuccinic acid (Ciba-Geigy Specialty Chemicals Corp.)	0.3
Trimercapto-S-triazine sodium (Sankyo Kasei Co., Ltd.)	0.2
Polyethylene glycol #300 (NOF Corp.)	15.0
Xanthan gum (CP Kelco Aps)	0.4
Purified water	66.6
	100

Sodium fluoride, ammonium borofluoride, ammonium citrate, hydroxyacetic acid, tetrasodium ethylenediaminetetraacetate and
5 hydroxyethanediphosphonic acid, weighed out in the proportions listed in Table 2, were placed in a polyethylene container C, the total amount of purified water was added and stirring was effected for complete dissolution of the solid portion.

10 Next, polyoxyethylene lauryl ether, polyoxyethylene lauryl ether acetate, mercaptobenzothiazolesuccinic acid and trimercapto-S-triazine sodium, weighed out in the proportions listed in Table 2, were placed in a polyethylene container D, the polyethylene glycol #300
15 and xanthan gum were added and stirring was effected to obtain a uniform dispersion.

The dispersion of polyethylene container D was then added to and stirred in the polyethylene container C, and after addition of the total amount, stirring was
20 effected at 200 rpm for 3 hours to obtain a viscous liquid.

The liquid had a viscosity (measured at ordinary temperature with a Brookfield viscometer, at 30 rpm) of 700 mPa·s and a pH of 4.0. A small amount of 28 wt%
25 ammonia water was then added to adjust the pH to 5.0 for use as a discoloration removal cleaning agent (cleaning agent 2).

(Composition Example 3)

A discoloration removal cleaning agent of the
30 invention was prepared using the components shown in Table 3.

Table 3

Component	Content (wt%)
Sodium fluoride (Morita Chemical Industries Co., Ltd.)	1.0
Ammonium citrate (Fuso Chemical Co., Ltd.)	5.0
Hydroxyacetic acid (70 wt%) (U.S. DuPont Corp.)	4.0
Tetrasodium ethylenediaminetetraacetate (Chelest Corp.)	1.0
Hydroxyethanediphosphonic acid (Nippon Chemical Industrial Co., Ltd.)	1.0
Polyoxyethylene lauryl ether (Lion Corp.)	3.0
Polyoxyethylene lauryl ether acetate (Lion Corp.)	2.0
Mercaptobenzothiazolesuccinic acid (Ciba-Geigy Specialty Chemicals Corp.)	0.3
Trimercapto-S-triazine sodium (Sankyo Kasei Co., Ltd.)	0.2
Polyethylene glycol #300 (NOF Corp.)	15.0
Xanthan gum (CP Kelco Aps)	0.4
Alumina fine powder (Showa Denko K.K.)	20.0
Polytetrafluoroethylene (15 wt% dispersion (U.S. DuPont Corp.)	6.0
Purified water	41.1
	100

5

Sodium fluoride, ammonium citrate, tetrasodium ethylenediaminetetraacetate, hydroxyacetic acid and hydroxyethanediphosphonic acid, weighed out in the proportions listed in Table 3, were placed in a polyethylene container E, the total amount of purified water was added and stirring was effected for complete dissolution of the solid portion.

10

Next, polyoxyethylene lauryl ether, polyoxyethylene lauryl ether acetate, mercaptobenzothiazolesuccinic acid and polyethylene glycol #300, weighed out in the proportions listed in Table 3, were added to a polyethylene container F and stirred to a uniform mixed solution, and xanthan gum was added in small portions at a time to obtain a uniform dispersion.

15

The dispersion of polyethylene container F was then added to polyethylene container E while stirring, and

20

after addition of the total amount, the
polytetrafluoroethylene dispersion was further added and
stirring was effected at 200 rpm for 6 hours to obtain a
viscous liquid. Next, the alumina fine particles
5 weighed out in the listed amount were added to
polyethylene container E in small portions at a time,
and after the addition, stirring was effected at 200 rpm
for 2 hours to obtain a uniform viscous liquid.

The liquid had a viscosity (measured at ordinary
10 temperature with a Brookfield viscometer, at 30 rpm) of
3200 mPa·s and a pH of 4.5. A small amount of 28 wt%
ammonia water was then added to adjust the pH to 5.0 for
use as a discoloration removal cleaning agent (cleaning
agent 3).

15 (Example 1)

A test sample was prepared using a cold-rolled
TP270C titanium building material conforming to JIS
H4600, surface-finished by annealing in an argon gas
atmosphere and having the annealed surface dull finished
20 by roll calendering with a dull roll. This material
which had been exposed to an outdoor environment for 7
years was cut into samples with dimensions of 1.2 mm
thickness, 60 mm width and 80 mm length according to JIS
K2246 4.2.1. The hue of each of the test samples was
25 light black with a shade of purplish-gold, and the
thickness of the hue was 70-80 nm (as measured using an
auger electron spectrometer by JEOL Co., Ltd.). The
same titanium building material without outdoor exposure
was used for the basis of evaluation by the following
30 visual examination.

The discoloration removal cleaning agents prepared

in Composition Examples 1 and 2 (cleaning agents 1 and 2) were used for a removal cleaning test on the discolored sections of the aforementioned samples. The samples were evenly coated with the discoloration removal cleaning agents 1 and 2 using a bristle brush. The coating coverage of cleaning agent 1 was 65-70 g/m², and the coating coverage of cleaning agent 2 was 95-100 g/m². The cleaning agents were water washed using tap water for aging times of 15, 30 and 45 minutes after coating and then dried, and changes in the discolored sections of the samples were visually examined.

As a comparative example, a cleaning test was also conducted using a commercially available neutralizing agent (Mama Lemon, product of Lion Corp.), producing the results shown as Comparative Example 1. A sponge was used to evenly coat a test sample, and a sponge was also used to clean the test sample surface under flowing tap water, with aging times of 15, 30 and 45 minutes after coating.

The discolored sections of the cleaned test samples were evaluated visually by at least five evaluators. Almost all of the evaluators confirmed that the samples treated after an aging time of 30 minutes using cleaning agent 1 or cleaning agent 2 were comparable to the unexposed test sample.

Table 4 shows the results of the discoloration removal test. The proportion of discoloration removed was evaluated using a 50 x 50 mm measurement area of the measurement sheet, according to JIS K2246 Salt Spray Test 4.3.4. The evaluation was conducted on a 3-level scale of A, B and C, with evaluation of A for a test

sample with no discoloration compared to the unexposed material, evaluation of B for a test sample with thin discoloration remaining (remaining on greater than 0% and less than 10% of the area), and evaluation of C for a test sample with discoloration remaining on 10-20% of the area. The values in parentheses to the right of the letters of evaluations A-C are the results of color difference measurement before and after the cleaning test, and the color difference $[\Delta E = ((L^*_2 - L^*_1)^2 + (a^*_2 - a^*_1)^2 + (b^*_2 - b^*_1)^2)^{1/2}]$ before and after the test was used as the basis for evaluating the discoloration resistance. Here, L^*_1 , a^*_1 and b^*_1 represent the measurement results for the hue before the discoloration test, and L^*_2 , a^*_2 and b^*_2 represent the measurement results for the hue after the discoloration test, based on the $L^*a^*b^*$ color index specified in the method of JIS Z8729.

Table 4

	Aging time after coating of cleaning agent (ordinary temperature)		
	After 15 minutes	After 30 minutes	After 45 minutes
Discoloration sample coated with Comp.Ex.1	C ($\Delta E = 25.4$)	C ($\Delta E = 24.7$)	C ($\Delta E = 23.8$)
Discoloration sample coated with cleaning agent 1	C ($\Delta E = 14.3$)	A ($\Delta E = 3.4$)	A ($\Delta E = 3.2$)
Discoloration sample coated with cleaning agent 2	B ($\Delta E = 8.3$)	A ($\Delta E = 2.8$)	A ($\Delta E = 2.7$)
Discoloration sample coated with cleaning agent 3	B ($\Delta E = 7.9$)	A ($\Delta E = 2.6$)	A ($\Delta E = 2.5$)

(Example 2)

A test sample was prepared using a cold-rolled TP270C titanium building material conforming to JIS H4600, surface-finished by annealing in an argon gas

atmosphere, and exposed to an outdoor environment for 7 years. The material was cut into samples with dimensions of 1.2 mm thickness, 60 mm width and 80 mm length. It was then coated with cleaning agent 3 using a painting sponge roller. The coating coverage was 110-120 g/m².

After coating, the sample was immediately subjected to polishing with repeated movements of 10, 30 and 50 strokes using a polishing tool with a urethane nonwoven fabric and then cleaned with tap water, after which the proportion of discoloration was visually examined. Almost all of five or more evaluators conducting the visual examination confirmed that the test sample subjected to 30 polishing strokes was comparable to the unexposed test sample.

Table 5

	Number of polishing strokes with urethane nonwoven fabric after coating of cleaning agent		
	10 strokes	30 strokes	50 strokes
Discolored sample coated with cleaning agent 3	C	A	B

20

Table 5 shows the results of the discoloration removal test. The evaluation was conducted on a 3-level scale of A, B and C, with evaluation of A for a test sample with no discoloration compared to the unexposed material, evaluation of B for a test sample with no discoloration but slight scuffing remaining on 5-10% of the area, and evaluation of C for a test sample with light discoloration remaining on 10-20% of the area.

25

INDUSTRIAL APPLICABILITY

The discoloration removal cleaning agent for discolored sections of titanium building materials according to the present invention is industrially applicable due to its numerous effects including the following (1) to (4).

(1) A discoloration removal cleaning agent is provided which allows removal of discolored sections on titanium and titanium alloy building materials by water washing.

(2) The discoloration removal cleaning agent of the invention provides discoloration-free protection for prolonged periods due to the function of a fluoracarbon resin film and discoloration inhibitor which impart excellent discoloration resistance to areas of titanium and titanium alloy building materials which have been cleaned by a simple operation. That is, it provides an anti-discoloration property which persists until the next cleaning, even under conditions of contact with highly polluted environments such as large cities.

(3) In the cleaning operation using the discoloration removal cleaning agent of the invention, no special experience is required for removal of discolored sections produced on the surfaces of titanium and titanium alloy building materials which have been in use for prolonged periods, such as outdoor roofs and walls, while an excellent discoloration removal effect is exhibited.

(4) The cleaning operation using the discoloration removal cleaning agent of the invention can be carried

out on roofs and their adjacent walls which are made of titanium and titanium alloy building materials, in a satisfactory working environment without scattering or dripping of the discoloration removal cleaning agent.

- 5 The drainage water obtained from water washing may be neutralized with aqueous slaked lime and subjected to treatment for separation of the precipitate using a flocculating agent or the like.

CLAIMS

1. A discoloration removal cleaning agent for titanium and titanium alloy building materials, which comprises at least a water-soluble inorganic acid salt,
5 an organic acid or organic acid salt, a surfactant, a hydrophilic oxygen-containing hydrocarbon solvent, and water.

2. The discoloration removal cleaning agent for titanium and titanium alloy building materials according
10 to claim 1, wherein said cleaning agent also satisfies either or both of the following conditions (1) and (2):

(1) Said cleaning agent comprises one or more types of thickener;

(2) The viscosity of said cleaning agent
15 (measured at room temperature with a Brookfield viscometer) is 100-10,000 mPa.s.

3. The discoloration removal cleaning agent for titanium and titanium alloy building materials according to claim 1 or 2, wherein said cleaning agent also
20 satisfies either or both of the following conditions (3) and (4):

(3) Said cleaning agent comprises one or more types of fluoracarbon resin and one or more types of polishing material;

(4) Said cleaning agent comprises one or more
25 types of discoloration inhibitor.

4. The discoloration removal cleaning agent for titanium and titanium alloy building materials according to claim 3, wherein the content of inorganic fluorine
30 compound salts is 0.5-5.0 wt%.

5. The discoloration removal cleaning agent for

titanium and titanium alloy building materials according to any one of claims 1 to 4, wherein the organic acid or organic acid salt is at least one selected from the group consisting of formic acid, oxalic acid, citric acid, malic acid, lactic acid, tartaric acid, succinic acid, fumaric acid, gluconic acid, hydroxybutyric acid, ethylenediaminetetraacetic acid, hydroxyethylenediaminetetraacetic acid, diethylenetriaminopentaacetic acid, hydroxyethanediphosphonic acid, or salts such as sodium, potassium and ammonium salts of these organic acids.

6. The discoloration removal cleaning agent for titanium and titanium alloy building materials according to any one of claims 1 to 5, wherein the content of the organic acid or organic acid salt is 2-15 wt%.

7. The discoloration removal cleaning agent for titanium and titanium alloy building materials according to any one of claims 1 to 6, wherein the surfactant has an HLB (hydrophilic-lipophilic balance) value of 12 or greater.

8. The discoloration removal cleaning agent for titanium and titanium alloy building materials according to any one of claims 1 to 7, wherein the organic acid or organic acid salt is at least one selected from the group consisting of anionic surfactants such as polyoxyethylenealkyl ether acetic acids and their sodium salts, polyoxyethylenealkyl ether phosphoric acids and their sodium salts, dialkylsulfosuccinic acids and their sodium salts, and nonionic surfactants such as polyoxyethylenealkyl ethers, polyoxyethylenealkylallyl ethers and polyoxyethylenepolyoxypropylenealkyl ethers.

9. The discoloration removal cleaning agent for titanium and titanium alloy building materials according to any one of claims 1 to 8, wherein the content of the surfactant is 2-10 wt%.

5 10. The discoloration removal cleaning agent for titanium and titanium alloy building materials according to any one of claims 1 to 9, wherein the hydrophilic oxygen-containing hydrocarbon is at least one selected from the group consisting of ethylene glycol,
10 polyethylene glycol, propylene glycol, lower molecular weight polypropylene glycol, hexylene glycol, 1,3-butanediol, glycerin, methyldiglycol, methyltriglycol, ethyldiglycol, ethyltriglycol, butyldiglycol, butyltriglycol and N-methylpyrrolidone.

15 11. The discoloration removal cleaning agent for titanium and titanium alloy building materials according to any one of claims 1 to 10, wherein the content of the hydrophilic oxygen-containing hydrocarbon is 5-20 wt%.

 12. The discoloration removal cleaning agent for
20 titanium and titanium alloy building materials according to any one of claims 1 to 11, wherein the thickener is at least one selected from the group consisting of polyvinyl alcohol, methyl cellulose, hydroxyethyl cellulose, guar gum, xanthan gum, carboxyvinyl polymer,
25 polyethylene oxide and polyvinylpyrrolidone.

 13. The discoloration removal cleaning agent for titanium and titanium alloy building materials according to any one of claims 1 to 12, wherein the content of the thickener is 0.2-1.5 wt%.

30 14. The discoloration removal cleaning agent for titanium and titanium alloy building materials according

to any one of claims 1 to 13, wherein the discoloration inhibitor is at least one selected from the group consisting of mercaptobenzothiazole-based, triazole-based, imidazole-based and thiourea-based discoloration inhibitors.

15. The discoloration removal cleaning agent for titanium and titanium alloy building materials according to any one of claims 1 to 14, wherein the content of the discoloration inhibitor is 0.1-1.5 wt%.

10 16. The discoloration removal cleaning agent for titanium and titanium alloy building materials according to any one of claims 1 to 15, wherein the fluoracarbon resin is at least one selected from the group consisting of polytetrafluoroethylene, polytetrafluoroethylene-hexafluoropropylene copolymer and polyvinylidene fluoride.

17. The discoloration removal cleaning agent for titanium and titanium alloy building materials according to any one of claims 1 to 16, wherein the content of the fluoracarbon resin is 0.3-2.0 wt%.

18. The discoloration removal cleaning agent for titanium and titanium alloy building materials according to any one of claims 1 to 17, wherein the polishing material is at least one selected from the group consisting of diamond, emery, garnet, corundum, ruby, silica sand, silicon carbide, alundum, cerium oxide, zirconium oxide, γ -alumina and chromium oxide.

19. The discoloration removal cleaning agent for titanium and titanium alloy building materials according to any one of claims 1 to 18, wherein the content of the polishing material is 10-30 wt%.

20. The discoloration removal cleaning method for titanium and titanium alloy building materials, wherein discolored sections of a titanium or titanium alloy building material are coated with the discoloration removal cleaning agent according to any one of claims 1 to 19 and allowed to stand for a prescribed period of time, and then said cleaning agent is removed by water washing of the coated sections.

21. The discoloration removal cleaning method for titanium and titanium alloy building materials according to claim 20, wherein the discoloration removal cleaning agent coated on the discolored sections of the titanium or titanium alloy building material is removed by high-pressure water washing (approximately 30-100 kg/cm², approximately 10-50 L/min) or low-pressure spray water washing (equal to or less than approximately 10 kg/cm², approximately 5-30 L/min) after standing for a prescribed period of time.

22. The discoloration removal cleaning method for titanium and titanium alloy building materials according to claim 20 or 21, characterized in that said coated sections are subjected to polishing after said coating, if necessary after standing for a prescribed period of time, before water washing.

23. The discoloration removal cleaning method for titanium and titanium alloy building materials according to claim 22, wherein the discoloration removal cleaning agent is removed by water washing after polishing.

24. The discoloration removal cleaning method for titanium and titanium alloy building materials, according to any one of claims 20 to 23, wherein the

coating coverage of the discoloration removal cleaning agent is 50-200 g/m².

ABSTRACT

A removal cleaning agent for discolored sections of titanium building materials which comprises at least a water-soluble inorganic acid salt, an organic acid or organic acid salt, a surfactant and a hydrophilic oxygen-containing hydrocarbon solvent, and optionally an discoloration inhibitor, fluoracarbon resin and polishing material. In the cleaning method for discolored sections of titanium building materials, coating is carried out with a bristle brush and a sponge roller, the coated film sections are polished with a nonwoven fabric or foam resin, optionally after aging, and then the discolored sections are removed by washing with water.